

Supplementary material

Reversible exchange of stable nitroxyl radicals on nanosilver particles

Mark A. Chappell,^{A,B} Lesley F. Miller^A and Cynthia L. Price^A

^AEnvironmental Laboratory, US Army Engineer Research & Development Center, 3909 Halls Ferry Road, Vicksburg, MS 39180, USA.

^BCorresponding author. Email: mark.a.chappell@usace.army.mil




Fig. S1. Calibration curve for the relationship between nanosilver (nAg) suspension mass concentration and suspension light transmission (measured as absorbance) at an incident wavelength of 620 nm. The equation of the line is $Abs = 0.0105 \text{ nAg concentration}$ and the coefficient of determination (R^2) is 0.999.